



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
http://www.chamaeleon/produktion.de

TECHNICAL DATA SHEET

COPPER SPRAY

Article number: 27011

Intended use: Car refinishing Product/ Lubricant

General characteristics: High quality spray with a high copper content to prevent wear and sticking of screwed connections which are exposed to very high temperatures.

Product characteristics:

- High thermal stability
- Resistant to chemicals and weather influences
- Corrosion preventive
- Excellent adhesion
- Prevents wear and sticking
- Simplifies the future removal
- Directed jetspray

Applications:

- Brake parts
- Exhaust parts
- Screwed connections, which are exposed to high temperature
- Battery Poles
- Thread of Spark Plugs

Physical and Chemical Characteristics:

Contents	: 400 ml
Basis	: EP Grease and small copper particles
VOC-content	: Approximately 69% w/w
Solid content	: Approximately 31% w/w
Colour	: Copper
Scent	: Characteristic
Appearance	: Paste
Relative density at 20°C	: 0,767 g/ml
Yield	: 1,26 g/sec
Vapour pressure at 20°C	: 3 to 4 bar
Temperature resistant	: -40°C to +1.100°C



Chamäleon GmbH
Rudolf-Diesel-Straße, 8a
69115 Heidelberg-Germany
Tel.: +49-(0)-6221 520440
Fax: +49-(0)-6221 520449
E-mail: info@chamaeleon/produktion.de
<http://www.chamaeleon/produktion.de>

Usage:

Before use, carefully read the directions on the packaging and act accordingly. The aerosol should have room temperature. Best processing temperature 5 to 30°C. Before use, shake the aerosol. Apply copper spray. The specific lubrication property is achieved after evaporation of the solvent (approximately 1 minute).

Data: 05, October 2014

This release replaces all eventually earlier issued versions.

For the additional information that is not included to the Technical Data Sheet apply to the supplier: e-mail: info@chamaeleon-produktion.de

See information on safety in Safety Data Sheet.